

IN THE CLAIMS

Please substitute claims 1-14 with the following:

1. (Previously Presented) A magnetic head using magnetoresistive effect comprising:

a magnetic sensing portion formed of a magnetoresistive effect element, wherein:

said magnetic sensing portion includes a lamination layer structure portion in which at least a free layer made of a soft magnetic material of which the magnetization is rotated in response to an external magnetic field, a fixed layer made of a ferromagnetic material, an antiferromagnetic layer for fixing the magnetization of said fixed layer and a spacer layer interposed between said free layer and said fixed layer are laminated with each other;

said lamination layer structure portion further includes a magnetic flux introducing layer of which the tip end is opposed to a surface which is brought in contact with or opposed to a magnetic recording medium;

said lamination layer structure portion has at its lamination layer direction opposing side surfaces formed of one flat surface or continuous one curved surface over at least said free layer, said spacer layer and said fixed layer;

a hard magnetic layer having high resistance or low resistance for maintaining a magnetic stability of said free layer is disposed in direct contact with said opposing surfaces or through an insulating layer;

a sense current for said lamination layer structure portion flows through the lamination layer direction of said lamination layer structure portion; and

an external magnetic field is applied to the direction extended along the plane direction of said lamination layer structure portion and which is extended substantially along said opposing side surfaces.

2. (Previously Presented) A magnetic head using magnetoresistive effect comprising:

a magnetic sensing portion formed of a magnetoresistive effect element, wherein:

said magnetic sensing portion includes a lamination layer structure portion in which at least first and second fixed layers made of ferromagnetic materials, first and second antiferromagnetic layers for fixing the magnetizations of said fixed layers and first and second spacer layers interposed between free layers and said first and second fixed layers are laminated with each other across both surfaces of said free layers made of soft magnetic materials of which the magnetizations are rotated in response to an external magnetic field;

said lamination layer structure portion further includes a magnetic flux introducing layer of which the tip end is opposed to a surface which is brought in contact with or opposed to a magnetic recording medium;

said lamination layer structure portion has at its lamination layer direction opposing side surfaces formed of one flat surface or continuous one curved surface over at least said free layer, said spacer layer and said fixed layer;

a hard magnetic layer having high resistance or low resistance for maintaining a magnetic stability of said layer is disposed in direct contact with said opposing surfaces or through an insulating layer;

a sense current for said lamination layer structure portion flows through the lamination layer direction of said lamination layer structure portion; and

an external magnetic field is applied to the direction extended along the plane direction of said lamination layer structure portion and which is extended substantially along said opposing side surfaces.

3. (Previously Presented) A magnetic head using magnetoresistive effect according to claim 1 or 2, wherein said spacer layer is formed of a nonmagnetic conductive layer.

4. (Previously Presented) A magnetic head using magnetoresistive effect according to claim 1 or 2, wherein said spacer layer is made of a tunnel barrier layer.

5. (Currently Amended) A magnetic head using magnetoresistive effect according to claim 1 or 2, wherein said hard magnetic layer and said free layer are disposed in such a manner that a central portion in the a thickness direction of said hard magnetic layer substantially agrees with a central portion in the a thickness direction of said free layer.

6-12. (Cancelled).

13. (New) A magnetic head using magnetoresistive effect comprising:

a magnetic sensing portion formed of a magnetoresistive effect element, wherein:

said magnetic sensing portion includes a lamination layer structure portion in which at least a magnetic flux introducing layer made of a soft magnetic material of which the magnetization is rotated in response to an external magnetic field, a fixed layer made of a ferromagnetic material, an antiferromagnetic layer for fixing the magnetization of said fixed layer and a spacer layer interposed between said magnetic flux introducing layer and said fixed layer are laminated with each other, wherein a tip end of said magnetic flux introducing layer is

opposed to a surface which is brought in contact with or opposed to a magnetic recording medium;

said lamination layer structure portion has at its lamination layer direction opposing side surfaces formed of one flat surface or continuous one curved surface over at least said magnetic flux introducing layer, said spacer layer and said fixed layer;

a hard magnetic layer having high resistance or low resistance for maintaining a magnetic stability of said magnetic flux introducing layer is disposed in direct contact with said opposing surfaces or through an insulating layer;

a sense current for said lamination layer structure portion flows through the lamination layer direction of said lamination layer structure portion; and

an external magnetic field is applied to the direction extended along the plane direction of said lamination layer structure portion and which is extended substantially along said opposing side surfaces.

14. (New) A magnetic head using magnetoresistive effect comprising:

a magnetic sensing portion formed of a magnetoresistive effect element, wherein:

said magnetic sensing portion includes a lamination layer structure portion in which at least first and second fixed layers made of ferromagnetic materials, first and second antiferromagnetic layers for fixing the magnetizations of said fixed layers and first and second spacer layers interposed between magnetic flux introducing layers and said first and second fixed layers are laminated with each other across both surfaces of said magnetic flux introducing layers made of soft magnetic materials of which the magnetizations are rotated in response to an

external magnetic field, wherein a tip end of said magnetic flux introducing layer is opposed to a surface which is brought in contact with or opposed to a magnetic recording medium;

said lamination layer structure portion has at its lamination layer direction opposing side surfaces formed of one flat surface or continuous one curved surface over at least said magnetic flux introducing layer, said spacer layer and said fixed layer;

a hard magnetic layer having high resistance or low resistance for maintaining a magnetic stability of said layer is disposed in direct contact with said opposing surfaces or through an insulating layer;

a sense current for said lamination layer structure portion flows through the lamination layer direction of said lamination layer structure portion; and

an external magnetic field is applied to the direction extended along the plane direction of said lamination layer structure portion and which is extended substantially along said opposing side surfaces.